# STRIDEN BATTERIES

# GP12-12 12V 12Ah

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore maintenance-free and leak proof. Batteries should be used in an upright position only.



## **Battery Construction**


Component	Positive Plate	Negative Plate	Container	Cover	Safety Value	Terminal	Separator	Electrolyte
Raw Material	Lead Dioxide	Lead	ABS	ABS	Rubber	Copper	Fibreglass	Sulfuric Acid


### **General Features**

- Positive and negative plates in lead-calcium-tin alloy.
- Stable Quality & High Reliability
- Sealed Construction.
- Long Service Life.
- Maintenance-Free Operation
- Low Pressure Venting System
- Low Self Discharge
- U.L. Component Recognition
- Six Month Shelf Life at 20°C
- Design life 10 Years

#### **Dimensions and Weight**

Length (mm/inch)	151/5.94
Width (mm/inch)	98/3.86
Height (mm/inch)	95/3.74
Total Height (mm/inch)	101/3.98
Approx. Weight (kg/lbs)	3.67/8.10





Strident



50 Turbine Way, Eco Tech Business & Innovation Park, Swaffham, Norfolk, PE37 7XD Tel: +44 (0)1362 300102 | Fax: +44 (0)1362 300103 | Email: sales@strident.uk.com

## **Performance Characteristics**

- Nominal Voltage: 12V
- Number of Cells: 6
  - Nominal Capacity 77°F (25°C) 10 Hour Rate (10.0A, 10.8V): 12Ah 5 Hour Rate (17.5A, 10.5V): 10.25Ah 1 Hour Rate (66.2A, 9.60V): 8.14Ah
- Internal Resistance
  - Fully Charged Battery 77°F (25°C) 17m 0hms Self-Discharge
- 3% of capacity declined per month at 20° (average)
  - Operating Temperature Range Discharge: -20~60°C Charge: -10~60°C
  - Storage: –20~60°C
- Max. Discharge Current 77°F (25°C): 180A (5s)
- Short Circuit Current: 600A
- Charge methods: Constant Voltage Charge 77°F (25°C)
  Cycle use: 2.30-2.35VPC
  Maximum charging current: 4.8A
  Temperature Compensation: -30mV/°C
- Standby use: 2.23-2.27VPC Temperature compensation: -20mV/°C



#### www.strident.uk.com

# STRIDEN BATTERIES

# GP12-12 12V 12Ah(20hr)

### **Discharge Data**

Discharge Constant Current (Amperes at 77°F/25°C)									
End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	24h
1.60V	46.4	31.7	24.8	13.8	8.14	3.18	2.12	1.18	0.61
1.65V	45.0	30.8	24.3	13.5	8.04	3.15	2.10	1.17	0.61
1.70V	43.5	29.9	23.7	13.3	7.94	3.12	2.07	1.16	0.61
1.75V	42.1	29.0	23.2	13.0	7.85	3.09	2.05	1.14	0.60
1.80V	40.6	28.2	22.6	12.7	7.75	3.06	2.02	1.12	0.59

The above characteristics data are average values obtained withing three charge/discharge cycles, not the minimum values.

Discharge Constant Power (watts at 77°F/25°C)								
End Point Volts/Cell	5min	10min	15min	30min	1h	2h	3h	5h
1.60V	86.2	58.7	46.7	27.0	16.1	8.50	6.50	4.20
1.65V	84.1	57.7	46.0	26.6	16.0	8.42	6.44	4.17
1.70V	81.9	56.6	45.3	26.2	15.8	8.33	6.37	4.14
1.75V	79.8	55.6	44.6	25.8	15.7	8.25	6.31	4.11
1.80V	77.6	54.6	43.9	25.4	15.5	8.16	6.24	4.08

The above characteristics data are average values obtained withing three charge/discharge cycles, not the minimum values.

Strident



50 Turbine Way, Eco Tech Business & Innovation Park, Swaffham, Norfolk, PE37 7XD Tel: +44 (0)1362 300102 | Fax: +44 (0)1362 300103 | Email: sales@strident.uk.com


ISO 9001





www.strident.uk.com




## GP12-12 12V 12Ah(20hr)




















Strident

bsi.



50 Turbine Way, Eco Tech Business & Innovation Park, Swaffham, Norfolk, PE37 7XD Tel: +44 (0)1362 300102 | Fax: +44 (0)1362 300103 | Email: sales@strident.uk.com



TRIDENT